



# MC-DUR 1252

## Resistant, low-yellowing epoxy resin coating for multi-storey car parks

### Product Properties

- Two-component, flexible, pigmented epoxy resin coating for car park areas and for use in industrial areas
- Thick-coating, may be filled and strewn with oven-dried aggregates
- Good abrasion-, chemical- and UV-resistance

### Areas of Application

- Coating for interior and exterior parking areas
- For use in industrial areas or similar
- REACH-assessed exposure scenarios: periodical water-contact, periodical inhalation, application

### Application

#### Substrate Preparation/Mixing

See leaflets "General Application Advice": "Industrial Flooring - Substrate and Substrate Preparation" and "Reactive Resins".

#### Priming

MC-DUR 1200 VK, see technical data sheet "MC-DUR 1200 VK".

#### Scratch Coat

The scratch coat consists of MC-DUR 1200 VK and oven-dried quartz-sand (grain-size 0.1-0.3 mm). See technical data sheet "MC-DUR 1200 VK".

#### Application

MC-DUR 1252 is applied 12 to 24 hours after application of the scratch coat, using a float, pin screed or rubber squeegee and deaerated with a spiked roller. For a layer thickness of more than 1 mm MC-DUR 1252 can be filled with oven-dried quartz-sand (0.1 - 0.3 mm) in a mixing ratio of 1 : 0.5 parts by weight. Afterwards the still fresh areas are deaerated cross-wise with a spiked roller. For anti-skid surfaces the previously filled coating is strewn in excess (approx. 5 - 6 kg) with oven-dried quartz-sand (e.g. 0.2 - 0.7 mm or coarser) while still fresh. After curing the excess sand is removed and a top-sealer can be applied. The top sealer is applied sharply across the grains

using a rubber squeegee and rolled crosswise with a short-piled lambskin roller.

#### Application on vertical areas

For use on sloped and vertical areas MC-DUR 1252 is added approx. 3 - 5 weight-% MC-Stellmittel TX 19 (MC-Thixotropic Agent TX 19).

#### General Information

Coverage, application times, resistance to foot traffic and time until full resistance are determined by temperature and site properties and condition. See also leaflet "General Application Advice - Reactive Resins".

Concerning the batch colour consistency, please note the general information on the leaflet "General Application Advice - Reactive Resins".

Exposure to chemicals and UV-light may cause colour changes, which usually do not affect the properties and usability of the coating. Mechanically and chemically exposed surfaces are subject to wear and tear. Regular check-ups and continuous maintenance are advised.

Temperatures below 10 °C combined with relative humidity above 80 % during the curing phase may cause color and gloss differences in the coating surface, as well as an increased susceptibility to dirt.



## Technical Data for MC-DUR 1252

Characteristic	Unit	Value	Comments
Mixing Ratio	p. b. w.	5 : 1	base : hardener
Density	g/cm <sup>3</sup>	approx. 1.5	-
Viscosity	mPa s	approx. 2,500	at 20 °C and 50 % relative humidity
Pot Life	minutes	approx. 50	at 20 °C and 50 % relative humidity
Trafficable after...	hours	approx. 12	at 20 °C and 50 % relative humidity
Time until full resistance	days	7	at 20 °C and 50 % relative humidity
Tensile strength	N/mm <sup>2</sup>	approx. 12	at 23 °C (DIN 53455)
Application conditions	°C % K	≥ 10 - ≤ 30 ≤ 85 3	air, material and substrate temperature relative humidity above dew-point
Coverage	kg/m <sup>2</sup>	1.5	per mm layer thickness

## Product Characteristics for MC-DUR 1252

Cleaning agent	MC-Reinigungsmittel U
Standard Colour	MC-grey, RAL 7032, RAL 7023 further colours on request
Delivery	12 or 30 kg packs
Storage	Can be stored in cool (below 20 °C) and dry conditions for at least one year in original unopened packs. Protect from frost!
Disposal	Packs must be emptied completely.
EU-regulation 2004/42 (Decopaint standard)	RL2004/42/EG All/j (500 g/l) < 500 g/l VOC

### Safety Advice

Please take notice of the safety information and advice given on the packaging labels and safety information sheets and please take notice of the chapter "Safety Measures for Handling Coating Materials and Reactive Resins". GISCODE: RE1

**Note:** The information on this data sheet is based on our experiences and correct to the best of our knowledge. It is, however, not binding. It has to be adjusted to the individual structure, application purpose and especially to local conditions. Our data refers to the accepted engineering rules, which have to be observed during application. This provided we are liable for the correctness of this data within the scope of our terms and conditions of sale-delivery-and-service. Recommendations of our employees which differ from the data contained in our information sheets are only binding if given in written form. The accepted engineering rules must be observed at all times.

Edition 09/15. Some technical changes have been made to this print medium. Older editions are invalid and may not be used anymore. If a technically revised new edition is issued, this edition becomes invalid.