



MC-Fastpack EP solid

High Reactive Universal Adhesive for Rigid Binding of Concrete and Steel, Sealing and Coating

Product properties

- Ready-to-use 2-component epoxy-based duromer resin
- Thixotropic, stable, putty consistency
- Good adhesion on dry and humid mineral surfaces and metallic surfaces
- High tensile and compressive strength, rapid development
- Very low application temperature
- Comfortable processing of double chamber cartridges with MC-Fastpack Power-Tool

Areas of application

- Glueing of concrete and steel (e. g. anchors, mounting parts)
- Glueing of adhesion packers for injection (e. g. MC-Surfacepacker LP)
- Sealing of cracks at injection jobs, closing of cracks and flat joints
- Closing / levelling of bore holes, pores and cavities
- Small-scale coating repairs
- REACh-assessed exposure scenarios: periodical water-contact, periodical inhalation, application

Application

Preparation

The surface has to be sound and must be free of loose particles and parts that might debond. It can be dry to humid (change in colour due to presence of humidity, but no standing water).

Mixing of Components

MC-Fastpack EP solid consists of two components, component A and component B. Both components are delivered in ready-to-use double chamber cartridges. The volume ratio of the cartridge corresponds to the mixing ratio of 2 : 1. The mixing takes place in the static mixer of the cartridge system.

Application

The application of the adhesive from the cartridge is performed with MC-Fastpack Power-Tool. The mixed product must appear in uniform colour. Depending on the application MC-Fastpack EP solid can be processed with putty knives or steel floats.

After being applied, the adhesive should be carefully incorporated into the substrate. In drill

holes and anchor holes a redensification by a plug is recommended. The mixing head can be extended for application in deep holes.

The application time of MC-Fastpack EP solid is influenced by temperature of the material itself, layer thickness and substrate temperature. If the application is interrupted for longer than the application time, the static mixer should be replaced by a new one. Opened cartridges should be closed with the original sealing cap and used as soon as possible.

Special Note

Chemical stress and exposure to light may cause changes in colour that generally do not impair the serviceability.

Machine Cleaning

Within the application time all tools can be cleaned with MC-Verdünnung EP (MC-Thinner EP). Partially and completely cured material can only be removed mechanically.



Technical Data for MC-Fastpack EP solid

Characteristic	Unit	Value*	Comments
Mixing ratio	p.b.v.	2 : 1	component A : component B
Density	kg/dm ³	1.5	DIN EN ISO 2811-1
Viscosity component A component B mixture	Pa·s	approx. 100 approx. 35 approx. 80	EN ISO 3219
Consistency	-	pasty	stable up to approx. 10 - 15 mm
E-modulus	MPa	approx. 5.800	DIN EN ISO 178
Compressive strength	MPa	approx. 85	DIN EN ISO 604
Adhesive tensile strength (concrete)	MPa	≥ 2.5	DIN EN ISO 1542, 100 % break in concrete
Adhesive tensile strength development (blasted steel)	MPa	approx. 10 approx. 15 approx. 20	after 4 hours EN ISO 4624 after 8 hours EN ISO 4624 after 24 hours EN ISO 4624
Humidity of surface	-	dry up to slightly humid	mineral surfaces without pore water
Application time	minutes	approx. 7	depending on thickness of layer
Application conditions	°C % K	+ 2 to + 40 ≤ 90 3	air, material and substrate temperature relative humidity above dew point

* All technical values relate to 20 °C and 50 % relative humidity.

Product Characteristics for MC-Fastpack EP solid

Cleaning agent	MC-Verdünnung EP
Colour	Grey
Delivery	400 ml double chamber cartridges with a volume ratio of 2 : 1 8 cartridges in a box, 10 static mixers and 4 extension tubes.
Storage	Can be stored in original sealed cartridges at temperatures between + 5 °C and + 25 °C in dry conditions. The shelf life is at least one year. The same requirements are valid for transport.
Disposal	Cartridges must be emptied completely.

Service

Individual consultation for project specific application is offered by our technical service. This includes also our discharger and the static mixers. GISCODE: RE1

Note: The information on this data sheet is based on our experiences and correct to the best of our knowledge. It is, however, not binding. It has to be adjusted to the individual structure, application purpose and especially to local conditions. Our data refers to the accepted engineering rules, which have to be observed during application. This provided we are liable for the correctness of this data within the scope of our terms and conditions of sale-delivery-and-service. Recommendations of our employees which differ from the data contained in our information sheets are only binding if given in written form. The accepted engineering rules must be observed at all times.

Edition 10/13. Some technical changes have been made to this print medium. Older editions are invalid and may not be used anymore. If a technically revised new edition is issued, this edition becomes invalid.

②